

X-Pruf Roof Scrim

Reinforcing mesh for liquid applied waterproof membranes

60570110

Product Description

X-Pruf Roof Scrim is a alkali resistant glass fiber mesh used with liquid applied roof membranes to provide a reinforced membrane able to accommodate tensile stresses in the cured membrane.

Advantages

- High strength
- Easy to use
- Compatible with a wide range of liquid membranes
- Small mesh size

Uses

Reinforcement of liquid applied roof membrane.

Typical Properties

Property	Typical Results
Fabric weight	70g/m ²
Mesh size	2mm x 2mm
Tensile Strength	560N/5cm
Elongation	2.5%

Packaging

1m x 50m rolls

Installation Guidelines

X-Pruf Roof Scrim is embedded in to the first coat of the liquid membrane. Apply the membrane as per the manufacturers instructions. While the membrane is still workable (before initial set/cure) place the Roof Scrim on top of the membrane and allow to cure (it is ok if the Roof Scrim is not fully embedded). Then apply the second layer to fully embed the Roof Scrim. For single coat systems apply a thin coat first. Place the membrane then overcoat to the recommended film thickness. When overlaps cure required they should be 50mm wide.

Health and Safety

This product is not considered hazardous.

Authorized Technical Specialist

Please note that only X-Calibur Authorized Technical Specialists ('ATSS') are permitted to change any of the information in this data sheet or to provide written recommendations concerning the use of this product. Visit www.x-calibur.us for a full list of X-Calibur ATSS.

Datasheet Validity

X-Calibur makes modifications to its product datasheets on a continuous basis. Please check the datasheet update section on www.x-calibur.us to ensure you have the latest version.

Warranties

X-Calibur supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. X-Calibur does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to X-Calibur in writing within five working days of being detected. X-Calibur Construction Chemistry Inc. **makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied.** X-Calibur Construction Chemistry Inc. shall not be liable for damages of any sort including remote or consequential damages, down time, or delay.